

HE2551A is a thermoplastic, solvent-based acrylic resin.

Characteristics

It is used for one-component self-drying coatings at room temperature. It is suitable for toy paint, plastic paint, pigmented paint.

Delivery form

50% in toluene;

Product specifications

Solid Content:	48.0-52.0%
Sond Content.	10.0 52.070

Viscosity (25°C, NDJ rotational viscometer): 3.0-6.0 Pa.s

Color number $\leq 1\#$ (Fe-Co)

Acid value 8.0-14.0 mgKOH/g

Appearance clear and transparent

The following items are not required:				
Tg	50°C (calculated value)			
flash point	4°C			
density (20°C)	0.97-1.03 g/ml			

Principal properties

High gloss and good adhesion;

Excellent chemical resistance and good wettability to pigments.

Applications

It is suitable for toy paint, plastic paint, pigmented paint.

Compatibility with resins and solvents

HE2574	+	HE2580	+	xylene	+	2- butoxyethanol	+
HE2592	+	HE2560	+	toluene	+	120#	0
HE2582	+	HE2598	+	butyl acetate	+	isobutanol	+
CAB- 381-20	+	NC	+	cyclohe xanone	+	methyl ethyl ketone	+

Note: + means soluble/miscible; Omeans partially soluble/partially miscible;

- means insoluble/incompatible.

1.1 / 19.10.2023 (Replace all previous versions)

Reference recipe

white paint	diluent		
HE2551A	50	toluene	15
titanium dioxide	25	isopropanol	20
BYK110	1	butyl acetate	15
butyl acetate	10.7	isobutanol	15
BYK358	0.3	BCS	10
Xylene/BCS	13	ethyl acetate	25

Storage guidelines

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature no more than 30°C. Exposure to direct sunlight should be avoided.

Shelf life

Under above mentioned storage condition, the shelf life of the resin will be 365 days after production.

For more than 365 days, the goods are still owned by ZOHO Company, the company's QC can make the corresponding extension of the shelf life after testing qualified.

Material safety

This product data sheet only applies to the latest version of Material Safety Data Sheet. Any updates to safety-related information that are consistent with legal requirements will only be reflected in the safety data sheet, at the same time the Sheet will be updated and published. Information on current classification and labelling, application and process methods, and more safety-related data can be found in the latest Material Safety Data Sheet.

1/1

Disclaimer: ZOHO assumes no responsibility for any person's use of any information contained herein. The information contained in this sheet is only the best knowledge of the product held by ZOHO. It does not constitute a warranty of any kind as to the accuracy, completeness or relevance of the data listed herein. The sheet contained herein should not be construed as granting any license or right under any patent or other intellectual property right of ZOHO or any third party. Product information is for reference only. We make no warranties or guarantees as to the suitability of the products and/or information for any particular purpose, performance or results. Users should conduct self-testing in order to determine suitability for a particular purpose. The final selection of products and/or information and the investigation of any possible infringement of the intellectual property rights of ZOHO and/or third parties are the sole responsibility of the user.