

HE2599 is a thermoplastic, solvent-based acrylic resin.

### Characteristics

It is used for one-component self-drying coatings at room temperature. It is suitable for plastic aluminum powder paint with high hardness and high alcohol resistance requirements.

### Delivery form

50% in toluene/butyl acetate/isobutanol;

### Product specifications

Solid Content: 48.0–52.0%

Viscosity (25°C, NDJ rotational viscometer): 18.0- 35.0 Pa.s

Color number ≤ 1# (Fe-Co)

Acid value 0.0-3.0 mgKOH/g

Appearance clear and transparent

The following items are not required:

Tg 102°C (calculated value)

flash point 4°C

density (20°C) 0.97-1.03 g/ml

### Principal properties

High hardness, high wear resistance;

Excellent alcohol resistance;

Excellent arrangement performance of aluminum powder.

### Applications

It is suitable for plastic aluminum powder paint with high hardness and high alcohol resistance requirements.

### Compatibility with resins and solvents

|            |   |        |   |               |   |                     |   |
|------------|---|--------|---|---------------|---|---------------------|---|
| HE2574     | + | HE2580 | + | xylene        | + | 2-butoxyethanol     | + |
| HE2562     | + | HE2560 | + | toluene       | + | 120#                | ○ |
| HE2582     | + | HE2592 | + | butyl acetate | + | isobutanol          | + |
| CAB-381-20 | + | NC     | + | cyclohexanone | + | methyl ethyl ketone | + |

Note: + means soluble/miscible; ○ means partially soluble/partially miscible;

— means insoluble/incompatible.

### Reference recipe

| aluminum powder paint |     | diluent       |    |
|-----------------------|-----|---------------|----|
| HE2599                | 60  | toluene       | 15 |
| aluminum powder       | 10  | isopropanol   | 20 |
| 20%CAB-381-20         | 15  | butyl acetate | 15 |
| butyl acetate         | 7.7 | isobutanol    | 15 |
| BYK333                | 0.3 | BCS           | 10 |
| toluene               | 7   | ethyl acetate | 25 |

### Storage guidelines

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature no more than 30°C. Exposure to direct sunlight should be avoided.

### Shelf life

Under above mentioned storage condition, the shelf life of the resin will be 365 days after production.

For more than 365 days, the goods are still owned by ZOHO Company, the company's QC can make the corresponding extension of the shelf life after testing qualified.

### Material safety

This product data sheet only applies to the latest version of Material Safety Data Sheet. Any updates to safety-related information that are consistent with legal requirements will only be reflected in the safety data sheet, at the same time the Sheet will be updated and published. Information on current classification and labelling, application and process methods, and more safety-related data can be found in the latest Material Safety Data Sheet.