

HE3637 is a thermoset, solvent-based acrylic resin.

Characteristics

It is used to prepare hardware baking paint, metal pigmented baking paint, the primer of elastic paint, the primer of UV paint with amino resin.

Delivery form

60% in xylene/isobutanol;

Product specifications

Solid Content: 58.0–62.0%

Viscosity (25°C, NDJ rotational viscometer): 4.0-7.0 Pa.s

Color number ≤ 1# (Fe-Co)

Acid value 5.0-10.0 mgKOH/g

Appearance clear and transparent

The following items are not required:

flash point 25°C

density (20°C) 0.99-1.03 g/ml

Principal properties

Good pigment wettability;

Good matte powder arrangement;

Good adhesion to hardware and glass;

Good chemical resistance;

Good recoatability.

Applications

It is used to prepare hardware baking paint, metal pigmented baking paint, the primer of elastic paint, the primer of UV paint.

Compatibility with resins and solvents

HE3659	+	HE3640	+	xylene	+	2- Butoxyethanol	+
HE1762	+	HE3654	+	trimethy lbenzen e	+	CAC	+
HE3746	+	HE5968	+	butyl acetate	+	isobutanol	+
HE3646 E	+	HE1767	+	Cyclohe xanone	+	Methyl ethyl ketone	+

Note: + means soluble/miscible; ○ means partially soluble/partially miscible;

— means insoluble/incompatible.

Reference recipe

varnish		diluent	
HE3637	50	XYL	50
HE1762	20	Trimethylbenzene	10
BYK306	0.2	n-Butyl acetate	10
E44	4	CAC	15
isobutanol	4.8	isobutanol	15
XYL	13		
PMA	5		
Adherent ADP	2		

Storage guidelines

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature no more than 30°C. Exposure to direct sunlight should be avoided.

Shelf life

Under above mentioned storage condition, the shelf life of the resin will be 365 days after production.

For more than 365 days, the goods are still owned by ZOHO Company, the company's QC can make the corresponding extension of the shelf life after testing qualified.

Material safety

This product data sheet only applies to the latest version of Material Safety Data Sheet. Any updates to safety-related information that are consistent with legal requirements will only be reflected in the safety data sheet, at the same time the Sheet will be updated and published. Information on current classification and labelling, application and process methods, and more safety-related data can be found in the latest Material Safety Data Sheet.