

HE3865 is a thermoset, solvent-based acrylic resin.

Characteristics

It is used to prepare bicycle baking paint, metal baking paint, automobile wheel baking paint with amino resin.

Delivery form

80% in xylene/butyl acetate;

Product specifications

Solid Content: 78.0–82.0%

Viscosity (25°C, NDJ rotational viscometer): 5.0-10.0 Pa.s

Color number $\leq 1\#$ (Fe-Co)

Acid value 7.0-12.0 mgKOH/g

Appearance clear and transparent

The following items are not required:

flash point 22°C

density (20°C) 0.99-1.03 g/ml

Principal properties

High gloss and fullness;

High solid content;

Good leveling performance;

Good recoatability.

Applications

It is used to prepare bicycle baking paint, metal baking paint, automobile wheel baking paint.

Compatibility with resins and solvents

HE3659	+	HE3654	+	xylene	+	2- Butoxyethanol	+
HE1762	+	HE1767	+	trimethy lbenzene	+	CAC	+
HE3611	+	HE5968	+	butyl acetate	+	isobutanol	+
HE3646 E	+	HE3737	+	cyclohe xanone	+	Methyl ethyl ketone	+

Note: + means soluble/miscible; ○ means partially soluble/partially miscible;

— means insoluble/incompatible.

Reference recipe

varnish		diluent	
HE3865	50	xylene	50
HE1767	23	trimethylbenzene	10
BYK306	0.2	butyl acetate	10
LubrizolR2063	2	CAC	15
E-44	5	isobutanol	15
xylene /isobutanol	21.7		

Storage guidelines

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature no more than 30°C. Exposure to direct sunlight should be avoided.

Shelf life

Under above mentioned storage condition, the shelf life of the resin will be 365 days after production.

For more than 365 days, the goods are still owned by ZOHO Company, the company's QC can make the corresponding extension of the shelf life after testing qualified.

Material safety

This product data sheet only applies to the latest version of Material Safety Data Sheet. Any updates to safety-related information that are consistent with legal requirements will only be reflected in the safety data sheet, at the same time the Sheet will be updated and published. Information on current classification and labelling, application and process methods, and more safety-related data can be found in the latest Material Safety Data Sheet.