

HE5968 is a methyl etherified amino resin

Characteristics

It is used to mix with thermosetting acrylic resin, saturated polyester resin and alkyd resin to prepare solvent-based baking paint. It has high gloss appearance, high hardness, good adhesion and good flexibility, especially suitable for coil coatings, automotive paints and water-based baking paints.

delivery form

80% solid content

Product specifications

Solid Content:	78.0–82.0%
Viscosity (25°C):	2500-6500mPa.s
Color number	≅ 1# (Fe-Co)
Acid value	≅ 1 mgKOH/g
Appearance	clear and transparent
Free formaldehyde	≅ 1.2%

Principal properties

High gloss, high hardness and high solid content
Excellent chemical resistance and salt spray resistance;
Good adhesion, excellent compatibility.

Applications

It is used to mix with thermosetting acrylic resin, saturated polyester resin and alkyd resin to prepare solvent-based baking paint. It is suitable for coil coatings, automotive paints and water-based baking paints. The cured paint film has high hardness, high gloss, good adhesion, excellent mechanical properties and excellent chemical resistance.

Compatibility with resins and solvents

HE3659	+	HE3611	+	xylene	+	2-Butoxyethanol	+
HE3642	+	HE3654	+	trimethylbenzene	+	2-Ethoxyethyl acetate	+
HE3746	+	HE3657	+	Butyl acetate	+	isobutanol	+
HE3646E	+	1/2NC	—	Cyclohexanone	+	n-butanol	+

Note: + means soluble/miscible; ○ means partially soluble/partially miscible;

— means insoluble/incompatible.

Storage guidelines

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature no more than 30°C. Exposure to direct sunlight should be avoided.

Shelf life

Under above mentioned storage condition, the shelf life of the resin will be 12 months after production.

For more than 12 months, the goods are still owned by ZOHO Company, the company's QC can make the corresponding extension of the shelf life after testing qualified.

Material safety

This product data sheet only applies to the latest version of Material Safety Data Sheet. Any updates to safety-related information that are consistent with legal requirements will only be reflected in the safety data sheet, at the same time the Sheet will be updated and published. Information on current classification and labelling, application and process methods, and more safety-related data can be found in the latest Material Safety Data Sheet.