

# ZOHO<sup>®</sup> HE6552

HE6552 is a solvent-based acrylic polyol resin with 2.4% hydroxyl content (based on the theoretical calculation of non-volatile components)

## Characteristics

It is used to prepare solvent-based two-component polyurethane coatings mixed with aliphatic isocyanate curing agent. It has a wide range of compatibility. The resin is suitable for high-grade home appliance paint, motor shell paint, 3C product paint.

## **Delivery form**

50% in toluene / butyl acetate

## **Product specifications**

Solid Content: 48.0–52.0%

Viscosity (25°C, NDJ rotational viscometer): 2.0-5.0 Pa.s

Color number  $\leq 2\#$  (Fe-Co)

Acid value 2.0-6.0 mgKOH/g

Appearance clear and transparent

The following items are not required:

flash point 4°C

hydroxyl value 2.4% (based on the non-volatile components) density (20°C) 0.99-1.03 g/ml

#### Principal properties

Excellent adhesion to PC substrate; High hardness, high gloss; Excellent wear resistance (RCA resistance);

## Applications

It is mainly used in combination with Desmodur N75, N3390, N3600 and other curing agents, and can be used to prepare self-drying or low-temperature baking ABS/PC plastic paints, high-grade home appliance paint and 3C product paint.

## Compatibility with resins and solvents

HE6536	+	HE6570	+	xylene	+	2-Butoxyethanol	+
HE6672	+	HE6673	+	trimethylb enzene	+	2-Ethoxyethyl acetate	+
HE6530	+	HE6631	+	Butyl acetate	+	isobutanol	+
1/2NC	+	CAB-381- 20	+	Cyclohex anone	+	n-butanol	+

Note: + means soluble/miscible; Omeans partially soluble/partially miscible;

- means insoluble/incompatible.

1.1 / 19.10.2023 (Replace all previous versions)

# Reference recipe

Aluminum J	oaint	diluent			
(Part A)	)				
HE6552	65	xylene	45		
Aluminum powder	10	toluene	10		
BYK306	0.2	butyl acetate	20		
BYK333	0.1	РМА	10		
Butyl acetate	24.7	ethyl acetate	10		
(Part B) Bayer N3390	Part A:	Part B: thinner =100: 9	9.2: 80~100		

#### Storage guidelines

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature no more than 30°C. Exposure to direct sunlight should be avoided.

## Shelf life

Under above mentioned storage condition, the shelf life of the resin will be 730 days after production.

For more than 730 days, the goods are still owned by ZOHO Company, the company's QC can make the corresponding extension of the shelf life after testing qualified.

## Material safety

This product data sheet only applies to the latest version of Material Safety Data Sheet. Any updates to safety-related information that are consistent with legal requirements will only be reflected in the safety data sheet, at the same time the Sheet will be updated and published. Information on current classification and labelling, application and process methods, and more safety-related data can be found in the latest Material Safety Data Sheet.

1/1

Disclaimer: ZOHO assumes no responsibility for any person's use of any information contained herein. The information contained in this sheet is only the best knowledge of the product held by ZOHO. It does not constitute a warranty of any kind as to the accuracy, completeness or relevance of the data listed herein. The sheet contained herein should not be construed as granting any license or right under any patent or other intellectual property right of ZOHO or any third party. Product information is for reference only. We make no warranties or guarantees as to the suitability of the products and/or information for any particular purpose, performance or results. Users should conduct self-testing in order to determine suitability for a particular purpose. The final selection of products and/or information and the investigation of any possible infringement of the intellectual property rights of ZOHO and/or third parties are the sole responsibility of the user.