



### **Product Data Sheet**

HE6752 is a solvent-based acrylic polyol resin with 2.6% hydroxyl content (based on the theoretical calculation of non-volatile components)

#### Characteristics

It is used to prepare solvent-based two-component polyurethane coatings mixed with aliphatic isocyanate curing agent. It is suitable for PU topcoat, construction machinery paint, anti-corrosion paint and pigmented paint.

# Delivery form

70% in BAC/ xylene

### **Product specifications**

Solid Content: 68.0–72.0%

Viscosity (25°C, NDJ rotational viscometer): 10.0-15.0 Pa.s

Color number  $\leq 1 \# \text{ (Fe-Co)}$ 

Acid value 10.0-15.0 mgKOH/g

Appearance clear and transparent

The following items are not required:

flash point 22°C

hydroxyl value 2.6% (based on the non-volatile components)

density (20°C) 0.99-1.03 g/ml

### **Principal properties**

High gloss, high fullness, good leveling property;

Good weather resistance;

Excellent chemical resistance, excellent adhesion to metal.

#### **Applications**

It is mainly used in combination with Desmodur N75, N3390, N3600 and other curing agents, and can be used to prepare self-drying or low-temperature baking PU topcoat, construction machinery paint, anti-corrosion paint and pigmented paint.

#### Compatibility with resins and solvents

HE6631	+	HE6771	+	xylene	+	2-Butoxyethanol	+
HE6672	+	HE6530	+	S-100	+	CAC	+
HE6570	+	HE6650	+	BAC	+	PMA	+
HE6675	+	HE6791	+	CYC	+	n-butanol	+

Note: + means soluble/miscible; Omeans partially soluble/partially miscible;

- means insoluble/incompatible.

# Reference recipe

Two-compone	nt (varnish)	diluent				
(Part	A)					
HE6752	70	XYL	40			
BYK333	0.3	TOL	5			
10%T-12	0.4	BAC	25			
BYK306	0.1	CAC	15			
XYL	10	PMA	15			
BAC	19.2					
(Part B) Bayer N3390	Part A: Part B: thinner =100: 15: 80~100					

# Storage guidelines

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature no more than 30°C. Exposure to direct sunlight should be avoided.

#### Shelf life

Under above mentioned storage condition, the shelf life of the resin will be 730 days after production.

For more than 730 days, the goods are still owned by ZOHO Company, the company's QC can make the corresponding extension of the shelf life after testing qualified.

#### Material safety

This product data sheet only applies to the latest version of Material Safety Data Sheet. Any updates to safety-related information that are consistent with legal requirements will only be reflected in the safety data sheet, at the same time the Sheet will be updated and published. Information on current classification and labelling, application and process methods, and more safety-related data can be found in the latest Material Safety Data Sheet.

1.1 / 19.10.2023 (Replace all previous versions)

1/1